

## RFT2 DOUBLE COATED FOAM TAPE

RFT2 consists of closed-cell foam coated on both sides with an extremely aggressive rubber-based adhesive. The foam carrier is flexible and conformable for filling spaces and joining irregular surfaces. RFT2 bonds effectively to corrugated, chipboard, powder coated metals, most UV materials and plastics and include low surface energy.

### Product Information

Foam:	Crosslinked Polyethylene	Thickness (inch): .063
Adhesive:	Rubber Based DRP75	
Release Liner:	55# Bleached SCK	
Application Temperature (°F):	65 to 100	
Service Temperature (°F):	-20 to 150	

### Foam

### Typical Properties

### Test Method

Density (lb/ft³):	2.7 - 3.3	ASTM D3575
Compression Deflection (PSI):	25% 2.1 min	ASTM D3575
Compression Set (%):	50% 38.0 max	ASTM D3575
Tensile Strength (PSI):	MD 71.0 min	ASTM D3575
Tensile Strength (PSI):	CD 44.0 min	ASTM D3575
Elongation (% to break):	MD 148.0 min	ASTM D3575
Elongation (% to break):	CD 148.0 min	ASTM D3575
Tear Resistance (lb/in):	MD 8.0 min	ASTM D3575
Tear Resistance (lb/in):	CD 13.0 min	ASTM D3575

### Adhesive\*

### Typical Properties

### Test Method

180° Peel Adhesion (lb/in):	8.0 min	PSTC-101
Shear Resistance (hrs):		
1in², 72°F	10 lb load: 72.0 min	PSTC-107
Quick Stick (lb/in):	9.0 min	PSTC-5

MD = Machine Direction

CD = Cross Direction

\* Tests are performed on 2 mil PET

Outwater Industries, Inc. provides this information and recommendations for informative purposes only. The data is intended as a guide only and is presented without guarantees and without assumptions of liabilities resultant from the use of the information provided.