

NPAB-1-101010

NPAB-1-101010 is a removable foam tape made to remove cleanly from most hard non-delaminating surfaces even after extended periods of time. NPAB-1-101010 has a permanent adhesive on one side and a removable adhesive on the other side.

Product Information

| | | |
|-------------------------------|---|-------------------------|
| Foam: | Cross-linked Polyolefin | Thickness (inch): 1.000 |
| Adhesive: | Permanent Rubber Based DRP75 Removable Rubber Based DRP125 | |
| Release Liner: | Silicone Coated Paper | |
| Application Temperature (°F): | 65 to 100 | |
| Service Temperature (°F): | -20 to 150 | |

Foam

Typical Properties

Test Method

| | | |
|-----------------------------------|-------|------------|
| Density (lb/ft ³): | 2.0 | ASTM D3575 |
| Compression Deflection (PSI): 25% | 7.0 | ASTM D3575 |
| Compression Set (%): 50% | 16.0 | ASTM D3575 |
| Tensile Strength (PSI): | 35.0 | ASTM D3575 |
| Elongation (% to break): | 160.0 | ASTM D3575 |
| Tear Resistance (lb/in): | 7.0 | ASTM D3575 |

Adhesive*

Typical Properties

Test Method

| | <u>DRP75</u> | <u>DRP125</u> | |
|-----------------------------|----------------------|---------------|----------|
| 180° Peel Adhesion (lb/in): | 8.0 min | 2.5 min | PSTC-101 |
| Shear Resistance (hrs): | | | |
| 1in ² , 72°F | 10 lb load: 72.0 min | 100.0 min | PSTC-107 |
| Quick Stick (lb/in): | 9.0 min | 2.0 min | PSTC-5 |

MD = Machine Direction

CD = Cross Direction

* Tests are performed on 2 mil PET